

Applicant : Donald W. Petersen et al.  
Serial No. : 09/915,997  
Filed : July 26, 2001  
Page : 3

COPY OF PAPERS  
ORIGINALLY FILED

Attorney's Docket No.: 06317-038002

RECEIVED

FEB 28 2002

TECH CENTER 1600/2900

Pending Claims



1. A bone graft substitute composition, consisting essentially of:  
calcium sulfate;  
a mixing solution; and  
a plasticizing substance.
2. The composition of claim 1, wherein the calcium sulfate comprises calcium sulfate hemihydrate.
3. The composition of claim 1, wherein the plasticizing substance comprises a cellulose derivative.
4. The composition of claim 1, wherein the plasticizing substance is selected from a group consisting of sodium carboxymethylcellulose, methylcellulose, hydroxypropyl methyl cellulose, hydroxypropyl cellulose, ethylcellulose, hydroxyethylcellulose, and cellulose acetate butyrate.
5. The composition of claim 1, wherein the plasticizing substance comprises hydroxypropyl methyl cellulose.
6. The composition of claim 1, wherein the plasticizing substance comprises hydroxypropyl cellulose.
7. The composition of claim 1, wherein the plasticizing substance comprises hyaluronic acid.
8. The composition of claim 1, wherein the plasticizing substance comprises methylcellulose.

9. The composition of claim 1, wherein the mixing solution is selected from a group consisting of sterile water, inorganic salt, and cationic surface active agent.

10. The composition of claim 9, wherein the cationic surface active agent is selected from a group consisting of sodium chloride, phosphate buffered saline, potassium chloride, sodium sulfate, ammonium sulfate, ammonium acetate, and sodium acetate.

11. The composition of claim 1, wherein the mixing solution comprises sterile water.

12. The composition of claim 1, wherein the composition does not comprise a polymer matrix.

13. The composition of claim 1, wherein the composition does not comprise bone.

14. The composition of claim 1, consisting essentially of:  
100 parts by weight of the calcium sulfate;  
about 1.5 to about 8 parts by weight of the plasticizing substance; and  
about 25 to about 65 parts by weight of the mixing solution.

15. The composition of claim 1, consisting essentially of:  
100 parts of the calcium sulfate;  
about 5.25 parts by weight of the plasticizing substance; and  
about 33.6 parts by weight of the mixing solution.